资源环境与节能

含锌粉尘氢还原低碳高值化新路线构建

滕飞1,郭培民1*,朱德庆2,龙红明3,李凯4,王磊1,孔令兵1

(1. 钢铁研究总院先进钢铁流程及材料国家重点实验室, 北京 100081; 2. 中南大学资源加工与生物工程学院, 湖南长沙 410083; 3. 安徽工业大学冶金工程学院, 安徽 马鞍山 243002; 4. 河北远大中正生物科技有限公司, 河北石家庄 050700)

摘 要:对国内外钢厂的含锌粉尘综合利用理论及技术进行了分析,火法还原工艺基于以煤为载体的高温碳冶金,能耗高、碳排放量大、污染严重是其难以回避的共性问题,同时还带来次氧化锌回收利用产生的能耗高、环境负荷大等新问题。根据团队以往研究经验,并结合目前国内外对低碳冶炼的新要求,提出了含锌粉尘氢还原低碳排放高值化利用技术思路:通过氢还原,将含锌粉尘中的铁和锌、铅、铋等有价金属还原,还原后的锌、铅、铋以气体形态被氢气载体带走,实现金属铁与有色金属的分离,含氢烟气再通过梯级冷凝分离锌、铅等有色金属。同时开展了含锌粉尘制备球团、氢还原理论和试验、含锌蒸汽分离理论分析及金属铁磁选等研究工作,为该技术思路的实施提供了坚实的基础。新技术有望实现钢厂含锌粉尘的低碳化冶炼,同时还可以得到附加值更高的金属锌及其它金属产品。

关键词:含锌粉尘;氢还原;低碳排放;高值化利用

中图分类号: X757

文献标志码:A

DOI: 10.7513/j.issn.1004-7638.2023.05.015

文章编号:1004-7638(2023)05-0098-07 开放科学 (资源服务) 标识码 (OSID):



听语音 聊科研

A new low carbon high value route for hydrogen reduction of zinc containing dust

Teng Fei¹, Guo Peimin^{1*}, Zhu Deqing², Long Hongming³, Li Kai⁴, Wang Lei¹, Kong Lingbing¹

(1. State Key Laboratory for Advanced Iron and Steel Processes and Materials, Iron and Steel Research Institute, Beijing 100081, China; 2. School of Minerals Processing and Bioengineering, Central South University, Changsha 410083, Hunan, China; 3. School of Metallurgical Engineering, Anhui University of Technology, Ma'anshan 243002, Anhui, China; 4. Hebei Yuanda Zhongzheng Bio-Tech Co., Ltd., Shijiazhuang 050700, Hebei, China)

Abstract: In this paper, the theory and technology of comprehensive utilization of zinc containing dust in steel plants at home and abroad are analyzed. The pyrometallurgical process is based on high-temperature carbon metallurgy with coal carrier. High energy consumption, enlarged carbon emission and serious pollution are its common problems that are difficult to avoid. At the same time, it also produces new problems such as high energy consumption and heavy environmental load caused by the recovery and utilization of secondary zinc oxide. According to the research experience of the research team and combined with the new requirements for low carbon at home and abroad, this paper puts forward a new technical idea of high-value utilization of low-carbon emission by hydrogen reduction: Iron and valuable metals such as zinc, lead and bismuth in zinc containing dust are reduced by hydrogen reduction, and the reduced zinc, lead and bismuth are taken away by hydrogen carrier in the form of gas to realize the separation of metal iron and non-ferrous metals. Non-ferrous metals such as zinc and lead are separated from hydrogen containing flue gas by step condensation. The preparation of pellets from zinc containing dust, hydrogen reduction theory and testing,

收稿日期:2023-05-29

基金项目:国家自然科学基金项目(52104297);山西省科技重大专项计划揭榜挂帅项目(ZDJB08)。

作者简介:滕飞, 1987 年出生, 博士研究生, 高级工程师, 研究方向: 烧结、球团, E-mail: 13426292269@139.com; ^{*}通讯作者: 郭培民, 1975 年出生, 博士, 教授级高工, 博士生导师, 研究方向: 炼铁新技术, E-mail: guopm@pku.org.cn。

theoretical analysis of zinc containing steam separation and metal ferromagnetic separation have been carried out, which provides a feasible and solid foundation for the proposal of this technical idea. The new technology is promising to realize low-carbon smelting of zinc containing dust in steel plants, and can also obtain metal zinc and other metal products with higher added value.

Key words: zinc dust, hydrogen reduction, low carbon emission, high value utilization

0 引言

钢铁工业是我国经济发展的重要基础产业,也 是固废排放大户,在其冶炼过程中会产生大量粉尘。 据统计,钢铁企业各类粉尘产生量一般占钢铁产量 的 8%~12%, 而其中含锌粉尘约占 20%~30%[1-2]。 以此推算,2019年我国钢铁厂含锌粉尘排放量超过 2000万t。含锌粉尘中含有重金属,属于典型危废, 必须经过妥善处置。另一方面,含锌粉尘也是宝贵 的二次资源, 其主要含有铁 (20%~35%)、锌 (0.5%~ 40%)、铅(0.2%~8%)、碳(0.5%~30%)等有价元 素[3-5]; 此外, 因使用多金属伴生铁矿石, 云南、湖南 等南方钢厂高炉瓦斯灰 (泥) 中常含有铟 (0.01%~ 0.05%)、铋 (0.003% ~ 0.6%) 和锡 (0.001% ~ 0.25%) 等多种稀散金属,其含量甚至已高于原生矿工业品 位[6-7]。粗略估计,仅2019年我国钢厂排放的含锌 粉尘中,铁、锌、铅和碳含量便可分别达 600 万 t、 40万t、8万t和300万t以上,云湘赣粤四省高炉 尘泥中 In、Bi 和 Sn 含量分别达 450、3 000 t 和 1500 t以上,资源量十分可观。而同时,我国相关原 生矿产资源匮乏,长期依赖进口。

近几十年来,国内不少研究单位开展含锌粉尘处理的理论及技术研究,我国钢厂含锌粉尘利用已取得长足进步^[8]:从最早的粉尘堆放,到返回烧结利用、制备冷固结球团作为炼钢冷却剂,再到采用转底炉、回转窑等工艺处理粉尘。

最近一段时间,大气污染已成为我国重点生态问题。资源和能源短缺及全球变暖、环境恶化等问题使全世界承受了巨大压力。21世纪的钢铁工业面临的环境压力很大,我国尤其严重。我国钢铁工业要实现可持续发展,实现"双碳目标",无疑钢厂粉尘高效资源化利用是重要的环节之一,对推进钢铁工业的绿色化进程具有重要的意义。笔者所在团队根据以往研究经验并结合现在国内外对低碳的新要求,提出了新型的氢还原低碳排放高值化利用技术思路。

1 现有含锌粉尘脱锌及次氧化锌综合利用理论和工艺研究现状

国内外研究了铁还原及锌铅分离的热力学、动力学、锌钾钠脱除和烟气形成及含锌烟尘沉积特性、黏结机理及球团爆裂粉化等基础理论研究^[9-17],促进了回转窑工艺、转底炉工艺和还原熔分法的工业应用^[18-25]。

1.1 回转窑提锌

国内外致力于用回转窑工艺提锌(图 1),得到杂质含量较高的次氧化锌,需要后续提纯;同时得到品位不高的海绵铁渣,添加到烧结料中循环使用。回转窑工艺已在宝钢、马钢、新钢、昆钢、河北远大等多家企业得到广泛应用。该工艺对原料适应性较好,投资少、运行成本较低,生产效率较高。不少回转窑厂家出现易结圈、冶炼能耗高、金属铁产品质量不高等问题。




图 1 回转窑处理含锌粉尘提锌流程

Fig. 1 Zinc extraction process for treating zinc containing dust in rotary kiln

1.2 转底炉提锌

国内外数家大型钢厂采用转底炉工艺处理含锌 尘泥(图 2),生产次氧化锌和金属化球团,保障了钢 铁主流程的畅通,然而该工艺存在一些突出问题待 解决:①球团粉化率高(~30%),加速耐材侵蚀和炉 底增厚,特别是含锌、铅和碱金属烟尘易粘结和堵 塞换热器,降低了换热效率,并导致设备故障率较高; ②热效率低(40%~60%),大量热量被烟气带走,必 须在炉外予以回收利用;③球团金属化率60%~ 80%,全铁含量低、渣多;④经济性较差。

目前含锌粉尘处理工艺存在的一些问题(如粉化、结圈、设备故障率、经济性差等),可以通过优化加以改善。但由于这些工艺基于以煤为载体的高温碳冶金,能耗高、碳排放大、污染严重是其难以回避的共性问题,同时还产生了次氧化锌回收利用新难题。这些问题影响人们对美好环境的追求,亟需突破。

1.3 次氧化锌的综合利用现状

次氧化锌是含锌粉尘火法脱锌工艺的主要产品之一,除含有大量锌、铅外,还常含有铋、铟、锡等多种稀散金属,具有极高的综合利用价值。但其氟

氯有害元素含量高,严重危害锌电积过程,增加除杂分离成本,且过程污染严重^[9,26-29]。目前,次氧化锌综合利用流程是火法 (湿法) 脱氟氯—湿法浸出锌等有价元素。硫酸或氨水浸出工艺可制备各种等级的硫酸锌、碳酸锌、氧化锌等产品,在此过程中再利用组分的理化特性差异除杂和分离铋、铟等有价金属。本项目组开发了次氧化锌综合利用技术解决了多资源利用问题,具体流程如图 3 所示。然而处理过程环境负荷大、能耗较高。




图 2 转底炉处理钢厂含锌粉尘流程 Fig. 2 Treatment of zinc containing dust in steel plant by rotary hearth furnace

次氧化锌 漂洗脱氯 纯碱. 调碱 火法脱氟氯 高效洗涤 硫酸 溶液 中性浸出 低酸浸出 置换除铋 酸漂 →副产品: 粗铋 压滤 滤液 高酸浸出 →副产品: 铅精矿 氧化除铁 余热锅 多效蒸发器 萃取 副产品 炉蒸汽 两次置换 压滤 酸漂 心 反萃取 滤液 液 单效蒸发 下 离 新鲜水 液 液 中性浸出工序 心 硫酸 中和 浓缩结晶 液 降温罐 离心分离 酸漂 ·次置换 离心分离 余热锅 烘干 离心分离 炉蒸汽 次置换 副产品: 粗锡 热风干燥 副产品 副产品 KC1 NaCl 副产品:粗铟 粉状—水 造粒 -新鲜水 硫酸锌 热风干燥 密闭筛分 粉状-水硫酸锌

图 3 一种次氧化锌综合利用流程

Fig. 3 A comprehensive utilization process of secondary zinc oxide

含锌粉尘氢还原 2

2.1 氢还原高值化技术路线构建

氢能具有能量密度大、零污染、零排放、可再 生等特点,被视为21世纪最具发展潜力的清洁能源, 是人类的战略能源发展方向[30]。氢气属于高化学能 还原剂,其还原潜能速率约比一氧化碳高一个数量 级,因此由传统碳还原转向氢还原,具有更佳的热力 学和动力学条件[31]。利用氢冶金取代传统的碳冶金 是突破化石能源的障碍、减少 CO, 排放、实现清洁 生产非常有效的解决路径。

目前富氢气体已用于铁矿气基直接还原[31],包 括 Midrex、HYL、Finmet 等工艺,它们均采用天然 气重整制富氢气体。我国由于缺乏天然气,气基直 接还原铁没有发展起来。经过多年发展,国内外已 经开发多种制氢技术,包括电解制氢、水煤气制氢、 焦炉煤气或甲醇制氢,特别是再生电等有望取得 长足发展,将会解决大规模、低成本的绿氢制取 难题。

根据火法还原特点,还原过程本应产生金属锌、 铅、铟等,但由于冶炼工艺及装备,最终已还原成金 属态的有色金属又二次氧化成氧化锌等金属氧化物, 这就客观造成了含锌粉尘综合利用整体能耗高、环 境负荷大。因此必须构建还原气氛回收金属锌、铅 等的新型技术路线。同时考虑到氢的低碳清洁和快 速反应特点,本团队提出钢厂含锌粉尘氢还原低碳 高值化新思路:通过氢还原将含锌粉尘中的铁、锌、 铅和铋等有价金属还原,还原后的锌、铅、铋以气体 形态被氢气载体带走,实现金属铁与有色金属的分 离,含氢烟气再通过梯级冷凝分离锌、铅等有色金 属。技术路线见图 4。


氢还原的产物是水,可实现绿色冶炼。氢还原 过程一直处于还原气氛,即可将锌、铅等有色金属 元素以金属态回收,利用还原气体中组分、饱和蒸 气压及沸点的差异,可以得到纯的金属锌、铅等有 色金属,改变了回转窑、转底炉还原由于气氛的问 题只能得到锌、铅等氧化物中间产品的难题,大大 缩短流程,降低了后续富集分离的难度、成本和环 境负荷。

2.2 氢还原路线主要工序及研究基础

2.2.1 含锌粉尘制备球团

新路线工序之一是粉尘的球团制备,由于粉尘

成分波动大,特别是粉尘中碳含量差异大,因此需要 针对性地研究含锌粉尘造球过程的理论及技术装备 问题。研究团队已通过预润湿活化手段,在润湿时 间 10 min、造球时间 12 min、生球水分 14.8% 左右、 膨润土用量 1.0% 的条件下,制备的生球 0.5 m 落下 强度为 12.1 次, 抗压强度 46 N/个, 干球抗压强度高 达 157 N/个, 干燥粉化率小于 1%, 湿球和烘干球的 外观形貌见图 5。



钢厂含锌粉尘氢还原低碳高值化新思路

Fig. 4 New idea of hydrogen reduction of zinc containing dust in steel plant




图 5 含锌粉尘球团宏观形貌

Fig. 5 Macromorphology of pellets containing zinc dust

2.2.2 含锌粉尘球团氢还原

新路线工序之二是含锌粉尘球团的氢还原, 其有两大特点:含锌粉尘中含有碳,在氡还原过 程中,碳同时参与反应,与氢气产生协同效应,因 此反应过程既有内生的碳热直接还原,还有外来 的氢气还原;多组分参与的复杂反应过程,含锌粉 尘还原涉及到铁氧化物, 锌、铅、钾、钠等多种金 属氧化物还原,氟、氯等杂质元素也会影响还原

反应。

Zn 的熔点和沸点较低,分别为 $420 \, ^{\circ} \, ^{\circ} \, ^{\circ} \, ^{\circ}$ 由于锌蒸汽在还原气中的浓度低,实际锌挥发温度远低于沸点。其它有色金属也类似。

通过热力学计算可得氢气还原锌氧化物和铁氧化物的平衡气相组成与温度的关系如图 6 所示。对于高锌含锌粉尘,氧化锌 (体积分数 20%) 还原曲线与氧化铁还原曲线相交点对应的温度为 780 ℃。当体系温度高于 780 ℃时,氧化锌比氧化铁更容易还原。在 1000 ℃条件下,经过 60 min 的氢还原可以得到金属化率 95%,抗压强度 1 695 N/个,残锌含量仅为 0.03% 的高强度金属化球团。含锌粉尘氢还原后得到的金属化球团微观结构如图 7 所示,由金属铁、渣相、浮氏体和少量空隙组成。




图 6 H₂ 还原锌氧化物和铁氧化物的平衡气相组成 Fig. 6 Equilibrium gas phase composition diagram of zinc oxide and iron oxide reduced by H₂


2.2.3 含尘金属烟气分离

新路线工序之三是粉尘和金属态锌、铅等分离。普通铁矿的氢还原,还原尾气主要完成除尘等净化过程,而本体系高温尾气中含有 Zn(g)、Pb(g) 及氟化物、氯化物及粉尘等,在降温过程会出现气一液一固三相。根据锌、铅、铋等蒸发热力学数据,可以得到还原气氛下的金属蒸汽与氟化物和氯化物的平衡温度与含量关系如图 8 所示,从图 8 可见,利用物理特性的差异能够分离金属锌,其它混合金属也可进一步进行分离。

2.2.4 还原球团后处理

至于还原得到的金属化球团,含有一定的脉石,由于锌、铅、钾、钠等已经被脱除,球团完全可以作为钢厂的金属铁原料使用。如果球团脉石含量特别高,还可通过破碎、球磨和磁选得到金属铁粉,进一步提高产品的附加值。项目组已开发含锌粉尘还原

铁--磁选金属铁粉工艺路线,并已在多家企业生产应用,为氢还原含锌粉尘+磁选金属铁粉积累了坚实的理论和实践基础。



MF: 金属铁; Sp: 造
(a) 含锌粉尘金属化球团
扫描电镜照片

Wu: 浮氏体; P: 空隙 (b) 含锌粉尘金属化球团 扫描电镜伪彩图

图 7 氢还原后金属化球团的微观结构

Fig. 7 Microstructure of metallized pellets after hydrogen reduction




图 8 金属蒸汽与粉尘中氯化物和氟化物的平衡温度与含量 关系

Fig. 8 Relationship between equilibrium temperature and content of metal vapor and chlorides and fluorides

总的来说,通过氢气还原有望实现钢厂含锌粉 尘的低碳化冶炼,同时还可以得到附加值更高的金 属锌及其它金属产品。

3 结论

对国内外的钢厂含锌综合利用理论及技术进行了分析,并且提出了新型的氢还原低碳排放高值化利用技术思路:通过氢还原将含锌粉尘中的铁和锌、铅、铋等有价金属还原,还原后的锌、铅、铋以气体形态被氢气载体带走,实现金属铁与有色金属的分离,含氢烟气再通过梯级冷凝分离锌、铅等有色金属。开展了含锌粉尘制备球粒、氢还原理论和试验验证、含锌蒸汽分离理论及磁选等研究工作,为本技术思路的实施提供了坚实的基础。新技术有希望实现钢厂含锌粉尘的低碳化治炼,同时还可以得到附加值更高的金属锌及其它金属产品。

参考文献

- [1] Antunano N, Cambra J F, Arias P L. Hydrometallurgical processes for Waelz oxide valorisation An overview[J]. Process Safety and Environmental Protection, 2019, 129: 308–320.
- [2] She Xuefeng, Xue Qingguo, Wang Jingsong, *et al.* Comparison of zinc-bearing dust comprehensive utilization and treatment processes in iron and steel plant[J]. Ironmaking, 2010, 29(4): 56–62. (佘雪峰, 薛庆国, 王静松, 等. 钢铁厂含锌粉尘综合利用及相关处理工艺比较[J]. 炼铁, 2010, 29(4): 56–62.)
- [3] Lv W, Gan M, Fan X H, *et al.* Recycling utilization of zinc-bearing metallurgical dust by reductive sintering: Reaction behavior of zinc oxide[J]. JOM, 2019, 71(9): 3173–3180.
- [4] Zhang Shourong, Zhang Weidong. Solid waste resources treatment mode and development tendency of iron and steel enterprises in China[J]. Iron and Steel, 2017, 52(4): 1-6.
 (张寿荣, 张卫东. 中国钢铁企业固体废弃物资源化处理模式和发展方向[J]. 钢铁, 2017, 52(4): 1-6.)
- [5] Xu Lejiang. Face the challenge and achieve the transformation from a big steel country to a powerful steel country[J]. China Steel, 2012, (5): 7–10.

 (徐乐江. 直面挑战—实现转型—由钢铁大国走向钢铁强国[J]. 中国钢铁业, 2012, (5): 7–10.)
- [6] Zurner P, Frisch G. Leaching and selective extraction of indium and tin from zinc flue dust using an oxalic acid-based deep eutectic solvent[J]. ACS Sustainable Chemistry & Engineering, 2019, 7(5): 5300–5308.
- [7] Zhu Yaoping. Practice of recovery indium zinc and bismuth from gas ash from blast furnace[J]. Nonferrous Metals (Extractive Metallurgy), 2009, (6): 14–16. (朱耀平. 高炉瓦斯灰中铟锌铋的回收实践[J]. 有色金属(治炼部分), 2009, (6): 14–16.)
- [8] Guo Peimin. Discussion on disposal of zinc-bearing dust in iron and steel plant[N]. World Metals, 2017-6-27(B12). (郭培民. 钢厂含锌粉尘处理方式探讨[N]. 世界金属导报, 2017-6-27(B12).)
- [9] Buzin P J W K, Heck N C, Vilela A C F. EAF dust: An overview on the influences of physical, chemical and mineral features in its recycling and waste incorporation routes[J]. Journal of Materials Research and Technology, 2017, 6(2): 194–202.
- [10] Guo Peimin, Zhao Pei. Efficient utilization of metallurgical resources [M]. Beijing: Metallurgical Technology Press, 2012. (郭培民, 赵沛, 冶金资源高效利用[M]. 北京: 冶金工业出版社, 2012.)
- [11] Hu Xiaojun, Liu Junbao, Guo Peimin, *et al.* Thermodynamic analysis of the reduction of zinc ferrite with CO-CO₂[J]. Chinese Journal of Engineering, 2015, 37(4): 429–435. (胡晓军, 刘俊宝, 郭培民, 等. 铁酸锌气体还原的热力学分析[J]. 工程科学学报, 2015, 37(4): 429–435.)
- [12] Zhang H N, Li J L, Xu A J, *et al.* Carbothermic reduction of zinc and iron oxides in electric arc furnace[J]. Journal of Iron and Steel Research International, 2014, 21(4): 427–432.
- [13] Zhu D Q, Li S W, Pan J, *et al.* Migration and distributions of zinc, lead and arsenic within sinter bed during updraft pre-reductive sintering of iron-bearing wastes[J]. Powder Technology, 2019, 342: 864–872.
- [14] Lu Hua, Wu Shengli, Zhang Jianliang, *et al.* Forming dynamics of pellet made frozinc-bearing dust in steel plant[J]. Iron and Steel, 2017, 52(5); 5–12.

 (鲁华, 吴胜利, 张建良, 等. 钢厂含铁粉尘动力学成球性能[J]. 钢铁, 2017, 52(5); 5–12.)
- [15] Wang Dongyan, Chen Weiqing, Zhou Rongzhang, *et al.* Basic properties and pellet making process for iron and steel plant Zn-Pb bearing dust[J]. Journal of University of Science and Technology Beijing, 1998, (2): 113–116. (王东彦, 陈伟庆, 周荣章, 等. 钢铁厂含锌、铅粉尘基本物性及造球工艺[J]. 北京科技大学学报, 1998, (2): 113–116.)
- [16] Wu Y L, Jiang Z Y, Zhang X X, et al. Process optimization of metallurgical dust recycling by direct reduction in rotary hearth furnace[J]. Powder Technology, 2018, 326: 101–113.
- [17] He Huanyu, Chen Zhenhong, Cui Yifang, *et al.* Sediment of flus gas in direct reduction treated by zinc-bearing metallurgical dust[J]. Iron and Steel, 2015, 50(12): 80–84.

 (何环宇, 陈振红, 崔一芳, 等. 含锌冶金尘泥还原烟气沉积特性[J]. 钢铁, 2015, 50(12): 80–84.)
- [18] Lin X L, Peng Z W, Yan J X, *et al.* Pyrometallurgical recycling of electric arc furnace dust[J]. Journal of Cleaner Production, 2017, 149: 1079–1100.
- [19] Rieger J, Schenk J. Residual processing in the European steel industry: a technological overview[J]. Journal of Sustainable Metallurgy, 2019, 5: 295–309.
- [20] Mager K, Meurer U, Garcia-Egocheaga B, et al. Recovery of zinc oxide from secondary raw materials: new developments of the Waelz process [C]//In: Stewart D L., et al. (eds), Proceedings of the Fourth International Symposium on Recycling of

- Metals and Engineered Materials . The Minerals, Metals & Materials Society, 2000 : 329-344.
- [21] Takaya S, Kubota N, Watanabe H, *et al.* Recent development of EAF dust treating at Shisaka Smelting Co., Ltd. [C]//In: Siegmund A., *et al.* (eds), Pb Zn 2020: 9th International Symposium on Lead and Zinc Processing. The Minerals, Metals & Materials Series, Springer, Cham. 2020: 91–97.
- [22] Holtzer M, Kmita A, Roczniak A. The recycling of materials containing iron and zinc in the oxy cup process[J]. Arch. Foundry Eng. 2015, 15: 126–130.
- [23] Hillmann C, Sassen K J. Processing of zinc-bearing BOF dusts in a blast furnace[J]. World Steel, 2013, 13(5): 8–9, 54. (Hillmann C, Sassen K J. 高炉处理转炉含锌粉尘[J]. 世界钢铁, 2013, 13(5): 8–9, 54.)
- [24] Pang Jianming, Guo Peimin, Zhao Pei. Practice of new technology of treating blast furnace dust containing zinc and lead with rotary kiln[J]. China Nonferrous Metallurgy, 2013, 42(3): 19–24. (庞建明, 郭培民, 赵沛. 回转窑处理含锌、铅高炉灰新技术实践[J]. 中国有色冶金, 2013, 42(3): 19–24.)
- [25] Wu Yuliang, Jiang Zeyi, Zhang Xinxin, *et al.* Numerical simulation of the direct reduction of pellets in a rotary hearth furnace for zinc-containing metallurgical dust treatment[J]. International Journal of Minerals Metallurgy and Materials, 2013, 20(7): 636–644.
- [26] Lu Yongsuo, Ning Jianping, Ruan Haifeng, *et al.* Hydrometallurgical recovery of zinc and removal of chlorine and fluorine from zinc oxide dust[J]. Hydrometallurgy of China, 2016, 35(5); 422–426.
 (路永锁, 宁建平, 阮海丰, 等. 从次氧化锌烟尘中湿法回收锌及去除氟氯[J]. 湿法冶金, 2016, 35(5); 422–426.)
- [27] Luo Yongguang, Zhang Libo, Peng Jinhui, *et al.* Status and future trend of fluorine removal in hydrometallurgical process of zinc oxide dust[J]. China Nonferrous Metallurgy, 2013, 42(4): 39–43. (罗永光, 张利波, 彭金辉, 等. 氧化锌烟尘湿法治炼过程除氟现状与发展趋势[J]. 中国有色冶金, 2013, 42(4): 39–43.)
- [28] Antuñano N, Cambra J F, Arias P L. Fluoride removal from double leached Waelz oxide leach solutions as alternative feeds to zinc calcine leaching liquors in the electrolytic zinc production process[J]. Hydrometallurgy, 2016, 161: 65–70.
- [29] Li Z Q, Li J, Zhang L B, *et al.* Response surface optimization of process parameters for removal of F and Cl from zinc oxide fume by microwave roasting[J]. Trans. Nonferrous Met. Soc. China, 2015, 25: 973–980.
- [30] Xu Kuangdi. Low carbon economy and iron and steel industry[J]. Iron and Steel, 2010, 45(3): 1-9. (徐匡迪. 低碳经济与钢铁工业[J]. 钢铁, 2010, 45(3): 1-9.)
- [31] Guo Peimin, Zhao Pei. Theory and technology for fast metallurgy at low temperature [M]. Beijing: Metallurgical Technology Press, 2020.

(郭培民, 赵沛. 低温快速冶金理论及技术[M]. 北京: 冶金工业出版社, 2020.)

编辑 杨冬梅

钒钛磁铁矿非高炉冶炼技术及产业化研讨会在成都市召开

由国家钒钛产业联盟等五家单位联合主办、主题为"探索钒钛磁铁矿非高炉冶炼新工艺,促进战略资源高质化利用"的钒钛磁铁矿非高炉冶炼技术及产业化研讨会于9月15日在成都市召开。

据介绍,氢基直接还原的非高炉冶炼是未来钢铁行业实现双碳目标的重要技术路线之一,而基于钒钛 磁铁矿的非高炉冶炼技术难度、产业价值比普通矿要大得多。目前氢基直接还原技术基本由外商掌握,突破技术封锁,形成具有自主知识产权的相关核心技术和装备,对我国钢铁行业低碳发展和钒钛战略资源综合利用具有重大意义。

本次研讨会由中国钢铁工业协会、四川省经济和信息化厅指导,国家钒钛产业联盟、钒钛资源综合利用产业技术创新战略联盟、钒钛资源综合利用国家重点实验室、四川省钒钛钢铁产业协会、四川省金属学会五家单位联合主办,攀钢承办。来自鞍钢集团、中国宝武、首钢集团、中国科学院、钢研总院、北京科技大学、中冶赛迪、东北大学、重庆大学、中南大学等企事业单位、科研院所近 100 名领导、专家教授和嘉宾围绕主题深入研讨,共商钒钛磁铁矿非高炉冶炼大计。

摘自 https://www.pzhsteel.com.cn/index.php?s=/Home/Article/pg_jianjie/art_bm_id/101/fl/two/msg_id/6275